



Frosted Window Film

Product Information

Construction - Polymeric PVC
PVC Thickness - 80 micron
Liner Thickness - 50 micron PET
Adhesive - Solvent based acrylic (permanent)
Cores - All on 76mm cores

Shelf Life: 2 years (stored up to 25°C and 50% relative humidity), in original packing of the box.

Minimum Application Temperature: 15°C - 60°C

Minimum life application under vertical outdoor exposure (Asian Climate): 1-2 years

Technical Data:

Test Items	Test Result	Standard	Test Method
Peel (Kg/25mm), for 20 minutes (N/25mm), for 20 minutes	1.21-1.26 11.86-12.35		ASTMD-1000 on stainless steel
Initial Tack (ballnp.7/cm)	3-5		JIS on stainless steel
Peel Adhesion to liner (g/25mm)	3-4		PSTC-1 30cm/min
Cohesion (min) holding power	1430 ↑		PSTC-7
Dimension Stability % shrinkage: 48 hours at 70°C 48 hours at 150°C	MD: CD: MD: CD:	<0.5	10cm x 10cm sample mounted on aluminum
Surface Finish			gloss meter 60° reflection
Coating Thickness	23-24		
Total Thickness with adhesive (mm)	0.108-0.109		

Codes

R220

R2200

Standard Stock Sizes

1230mm x 50m

1530mm x 50m

ALL PRICES EXCLUDE 10% GST AND DELIVERY CHARGES

PLEASE NOTE – All information, recommendations and suggestions contained herein, without limitation, stated values (collectively the “information”) shall be used only as a guide by Purchaser and not for specification or any other purpose. The information does not constitute a warranty or guaranty of any type whatsoever. Purchase should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own tests. ALC shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser’s reliance on the information.